

Applicant: JIN SHEU ENTERPRISE CO., LTD.
8F-9, NO., 502, YUAN SHAN RD.,
ZHONGHE DIST., NEW TAIPEI CITY 23545,
TAIWAN
Attn: HEIDI

Date: Mar 14, 2018

Sample Description:

Several pieces of submitted samples said to be White heat transfer polyester lanyards.

Standard	: --
Buyer's Name	: WORLD WIDE
Colour	: WHITE
Vendor	: WORLD WIDE
Manufacturer	: CHINA
Supplier	: CHINA
Style No./Name	: --
P.O. No.	: --
Ref.	: HEAT TRANSFER POLYESTER LANYARD (100% POLYESTER) AGE RANGE: 3+
Country Of Origin	: MADE IN CHINA
Goods Exported To	: WORLD WIDE
Date Received/Date Test Started	: Refer To Following Remark
Date Final Information Confirmed	: --

Remark: No Sample Is Submitted For Testing, All Test Results Are Referred To Previous Report GZHT90769284 Dated Feb 08, 2018.


Conclusion:

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Total Lead (Pb) Content In Non-Surface Coating Materials	Pass
2.	Total Cadmium (Cd) Content	Pass

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch

Huang Ning, Andy
Assistant General Manager



1 Total Lead (Pb) Content In Non-Surface Coating Materials:

With Reference To CPSC-CH-E1001-08.3:2012/CPSC-CH-E1002-08.3:2012, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

ND

Applicant's Requirement In ppm
90

Remark: ppm = Parts Per Million
Detection Limit = 10ppm
ND=Not Detected

Tested Components: White Textile (Webbing).

2 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

< 10

Applicant's Limit In ppm
75

Remark: ppm = Parts Per Million
Detection Limit = 10ppm

Tested Components: White Textile (Webbing).

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

