

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS LTD.
NO.3-1, SOUTH GAOBU BLVD
GAOBU, DONGGUAN, CHINA
ZIP CODE: 523278

Date: Feb 08, 2018

Attn: LILY/NANCY

Sample Description:

Two (2) pieces of submitted samples said to be Yellow twill material.

Standard : --
Buyer's Name : WORLD WIDE
Colour : YELLOW
Vendor : WORLD WIDE
Manufacturer : CHINA
Supplier : CHINA
Style No./Name : --
P.O. No. : --
Ref. : YELLOW TWILL
AGE RANGE: 3+
Country Of Origin : MADE IN CHINA
Goods Exported To : WORLD WIDE
Date Received/Date Test Started : Jan 15, 2018
Date Final Information Confirmed: Jan 17, 2018

Conclusion:

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Color Fastness To Washing	Pass
2.	Total Lead (Pb) Content In Non-Surface Coating Materials	Pass
3.	Total Cadmium (Cd) Content	Pass

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch

Huang Ning, Andy
Assistant General Manager



- 1 Color Fastness To Washing (ISO 105 C06 A2S-2010, Single Test, 30 Minutes Mechanical Wash At 40°C In 0.4% ECE Reference Detergent And 0.1% Sodium Perborate Solution With 10 Steel Balls):

		<u>Applicant's Requirement</u>
Color Change	Grade 4-5	Min. 4 Grade
Color Staining		Min. 4 Grade
-Acetate	Grade 4-5	
-Cotton	Grade 4-5	
-Nylon	Grade 4-5	
-Polyester	Grade 4-5	
-Acrylic	Grade 4-5	
-Wool	Grade 4-5	

Remark: This Test Was Conducted At 3F, Hengyun Building, No.235 Kaifa Avenue, GETDD

- 2 Total Lead (Pb) Content In Non-Surface Coating Materials:

With Reference To CPSC-CH-E1001-08.3:2012/CPSC-CH-E1002-08.3:2012, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

	<u>Result In ppm</u>	<u>Applicant's Requirement In ppm</u>
	ND	90

Remark: ppm = Parts Per Million
Detection limit = 10ppm
ND=Not Detected

Tested Component: Yellow Twill.

3 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

	<u>Result In ppm</u>	<u>Applicant's Limit</u> <u>In ppm</u>
	< 10	75

Remark: ppm = Parts Per Million
Detection Limit = 10ppm

Tested Component: Yellow Twill.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

