

TEST REPORT Number: GZHT90769678

Date:

Feb 08, 2018

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS

LTD.

NO.3-1, SOUTH GAOBU BLVD GAOBU, DONGGUAN, CHINA

ZIP CODE: 523278 Attn: LILY/NANCY

Sample Description:

One (1) piece of submitted sample said to be Mixture ink for extra printing material.

Standard : -

Buyer's Name : WORLD WIDE

Colour : --

Vendor : WORLD WIDE

Manufacturer : CHINA Supplier : CHINA Style No./Name : --P.O. No. : --

Ref. : MIXTURE INK FOR EXTRA PRINTING

AGE RANGE: 3+

Country Of Origin : MADE IN CHINA Goods Exported To : WORLD WIDE Date Received/Date Test Started : Jan 15, 2018 Date Final Information Confirmed: Jan 17, 2018

Conclusion:

| <u>Index</u> | <u>Test Item</u>                | <u>Result</u>                   |
|--------------|---------------------------------|---------------------------------|
| 1.           | 19 Toxic Element Migration Test | Meet Applicant's<br>Requirement |
| 2.           | Toxic Elements Analysis         | Meet Applicant's<br>Requirement |
| 3            | Soluble Lead Content Test       | Pass                            |

Should you have any query on this report, you may contact at <a href="mailto:gzfootwear@intertek.com">gzfootwear@intertek.com</a>

Authorized By:

For Intertek Testing Services Shenzhen Ltd.

Guangzhou Branch

Huang Ning, Andy

Assistant General Manager



Page 1 Of 4



<u>TEST REPORT</u>
Tests Conducted (As Requested By The Applicant)

1 19 Toxic Element Migration Test

With Reference To EN71-3:2013+A1:2014 And Followed By Inductively Coupled Plasma Optical Emission Spectrometry (ICP/OES).

Number:

GZHT90769678

Category (III): Scraped-Off Toy Material

| Element                    | Result (Mg/Kg) | Limit   |
|----------------------------|----------------|---------|
|                            |                | (Mg/Kg) |
| Aluminium (Al)             | < 300          | 70000   |
| Antimony (Sb)              | < 10           | 560     |
| Arsenic (As)               | < 10           | 47      |
| Barium (Ba)                | 66             | 18750   |
| Boron (B)                  | < 50           | 15000   |
| Cadmium (Cd)               | < 5            | 17      |
| Chromium (III) (Cr III) ++ | < 10           | 460     |
| Chromium (VI) (Cr VI) ++   | < 0.1          | 0.2     |
| Cobalt (Co)                | < 10           | 130     |
| Copper (Cu)                | < 10           | 7700    |
| Lead (Pb)                  | < 10           | 160     |
| Manganese (Mn)             | < 10           | 15000   |
| Mercury (Hg)               | < 10           | 94      |
| Nickel (Ni)                | < 10           | 930     |
| Selenium (Se)              | < 10           | 460     |
| Strontium (Sr)             | < 100          | 56000   |
| Tin (Sn)                   | < 10           | 180000  |
| Organic Tin ++             | < 3.0          | 12      |
| Zinc (Zn)                  | < 100          | 46000   |

Remark: Mg/Kg = Milligram Per Kilogram

 $^{++}$  = Unless The Test Results Were Marked With "#" Or " $\Delta$ ", Chromium (III) & Chromium (VI) And Organic Tin Contents Were Not Directly Determined And Were Derived From Migration Results Of Total Chromium And Tin Respectively.

Tested Component: Mixture Ink.

<sup>-</sup> Organic Tin Test Result Was Expressed As Tributyl Tin.



<u>TEST REPORT</u>
Tests Conducted (As Requested By The Applicant)

## 2 Toxic Elements Analysis

With Reference To Section 4.3.5 Of The ASTM Standard Consumer Safety Specification On Toy Safety ASTM F 963-16, Acid Digestion And Extraction Methods Were Used And Toxic Elements Content Were Determined By Inductively Coupled Argon Plasma Spectrometry.

|                    | Result In ppm | Applicant's Limit In |
|--------------------|---------------|----------------------|
|                    |               | <u>ppm</u>           |
| Sol. Barium (Ba)   | 66            | 1000                 |
| Sol. Lead (Pb)     | ND            | 90                   |
| Sol. Cadmium (Cd)  | ND            | 75                   |
| Sol. Antimony (Sb) | ND            | 60                   |
| Sol. Selenium (Se) | ND            | 500                  |
| Sol. Chromium (Cr) | ND            | 60                   |
| Sol. Mercury (Hg)  | ND            | 60                   |
| Sol. Arsenic (As)  | ND            | 25                   |

Remark: Sol. = Soluble

ND = Not detected Detection limit = 10 ppm ppm = Parts Per Million

Tested Component: Mixture Ink.

## 3 Soluble Lead Content Test

Test Method: Japan Toy Safety Standard 2016 Part 3 Chemical Properties Clause 2.7, 2.12, Acid Extraction Method Was Used And Soluble Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result (mg/kg) Requirement (mg/kg)
<5

Number:

GZHT90769678

Remark: mg/kg = milligram per kilogram

Tested Component: Mixture Ink.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.



TEST REPORT
Tests Conducted (As Requested By The Applicant)



Number:

GZHT90769678