

Applicant: JIN SHEU ENTERPRISE CO., LTD.
8F-9, NO., 502, YUAN SHAN RD.,
ZHONGHE DIST., NEW TAIPEI CITY 23545,
TAIWAN
Attn: HEIDI

Date: Mar 14, 2018

Sample Description:

One (1) piece of submitted sample said to be Soft PVC, ATBC PVC material.

Standard : --
Buyer's Name : WORLD WIDE
Colour : --
Vendor : WORLD WIDE
Manufacturer : CHINA
Supplier : CHINA
Style No./Name : --
P.O. No. : --
Ref. : Soft PVC, ATBC PVC MATERIAL
AGE RANGE: 3+
Country Of Origin : MADE IN CHINA
Goods Exported To : WORLD WIDE
Date Received/Date Test Started : Refer To Following Remark
Date Final Information Confirmed: --

Remark: No Sample Is Submitted For Testing, All Test Results Are Referred To Previous Report GZHT90770237 Dated Feb 08, 2018.


Conclusion:

<u>Index</u>	<u>Test Item</u>	<u>Result</u>
1.	Total Lead (Pb) Content In Surface Coating	Pass
2.	Total Cadmium (Cd) Content	Pass
3.	Phthalate Content Test	Pass

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch

Huang Ning, Andy
Assistant General Manager



1 Total Lead (Pb) Content In Surface Coating

With Reference To CPSC-CH-E1003-09.1:2011, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

Applicant's Requirement In

ND

ppm
90

Remark: ppm = Parts Per Million
Detection Limit = 10ppm
ND=Not Detected

Tested Components: Brown Ink.

2 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

Result In ppm

Applicant's Limit In ppm

<10

75

Remark: ppm = Parts Per Million
Detection Limit = 10ppm

Tested Components: Brown Ink.

3 Phthalate Content Test:

With Reference To CPSC-CH-C1001-09.3: 2010, by Gas Chromatographic-Mass Spectrometric (GC-MS) Analysis.

No.	Substance	Result In (% (w/w))	Applicant's Limit (% (w/w)) (Max)
1	Dibutyl phthalate (DBP)	ND	0.1%
2	Butyl benzyl phthalate (BBP)	ND	0.1%
3	Di-2-ethylhexyl phthalate (DEHP)	ND	0.1%
4	Diisobutyl phthalate (DIBP)	ND	0.1%
5	Di-Iso-Nonyl Phthalate (DINP)	ND	0.1%
6	Di-N-Octyl Phthalate (DNOP)	ND	0.1%
7	Di-Iso-Decyl Phthalate (DIDP)	ND	0.1%
8	Dipentyl Phthalate(DNPP)	ND	0.1%
9	Di-n-hexyl phthalate (DnHP)	ND	0.1%
10	Bis (2-methoxyethyl) phthalate (DMEP)	ND	0.1%
11	Diisopentylphthalate (DIPP)	ND	0.1%
12	N-pentylisopentylphthalate (NPIPP)	ND	0.1%
13	1,2-benzenedicarboxylic acid, di-C6-8-branched alkyl ester, C7-rich(DIHP)	ND	0.1%
14	1,2-benzenedicarboxylic acid, di-C7-11 branched alkyl ester and linear alkyl ester (DHNUP)	ND	0.1%
15	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear	ND	0.1%
16	1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters	ND	0.1%
17	1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with $\geq 0.3\%$ of dihexyl phthalate (EC No. 201-559-5)	ND	0.1%
18	Di-cyclohexylphthalate (DCHP)	ND	0.1%
19	Di-n-pentyl Phthalate (DPENP)	ND	0.1%

Remark : Detection Limit = 0.01% (w/w)
 ND = Not Detected

Tested Components: Brown Ink.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

GZHT90777302

